

NPC GE-11

Japanese : NPC GE-11

Excellent properties

- Viscosity
- Noise reduction
- Extreme pressure (EP) performance

Items		Product Data	Test Method
Thickener	-	Lithium soap	-
Base oil	-	Refined mineral	-
Color	-	Light brown	-
Service temperature range, °C	-	- 15 to 130	-
Worked Penetration	25 °C	340 (NLGI NO.1)	JIS K 2220 7
Dropping point, °C	-	188	JIS K 2220 8
Copper corrosion	100 °C, 24 hrs	Pass	JIS K 2220 9
Evaporation loss, mass%	99 °C, 22 hrs	0.34	JIS K 2220 10
Oil separation, mass%	100 °C, 24 hrs	3.3	JIS K 2220 11
Oxidation stability, kPa	99 °C, 100 hrs	25	JIS K 2220 12

- * These values are typical properties and are not specifications.
- * The information contained herein is subject to change without notification.
- * Please refer to Safety Data Sheet for more information.

T-1909



WEBSITE : <http://www.nippeco.co.jp>
E-MAIL : welcome@nippeco.co.jp

Head office	4F Yaesu-doori Hata Bldg., 1-9-8 Hatchoubori, Chuo-ku, Tokyo	Phone +81-3-5542-2483
Osaka business office	7F No.5-shin-Osaka Bldg., 3-12-15 Nishinakashima, Yudogawa-ku, Osaka	Phone +81-6-6886-1261
Nagoya business office	8F Ichigo Fushimi Bldg., 1-18-24 Nishiki, Naka-ku, Nagoya	Phone +81-52-222-1311
Muroran business office	2F Miyagawa Bldg., 6-23-8 Washibetsu-cho, Noboribetsu City, Hokkaido	Phone +81-143-87-1111